सिपेट : स्कल फार एडवांस्ड रिसर्च इन पेटोकेमिकल्स (एस. ए. आर. पी) एडवांस्ड पॉलीमर डिसैन रिसर्च & डेवेलपमेन्ट रिसर्च लॉबोरेटोरी. (ए.पी.डी.डी.आर.एल)

रसायन एवं पेटोरसायन विभाग

रसायन एवं उर्वरक मंत्रालय, भारत सरकार

प्लॉट नंबर : ७ पि. हार्ट टेक रक्ष और एयरोस्पेस पार्क (आईटी सेक्टर), जलाहोवली, बेंगलुरू - 562149

ई-मेल : apddrl@cipet.gov.in

मख्यालय : सिपेट, गिंडी, चेन्नै - 600032



CIPET: SCHOOL FOR ADVANCED RESEARCH IN PETROCHEMICALS (SARP)-ADVANCED POLYMER DESIGN & DEVELOPMENT RESEARCH LABORATORY (APDDRL)

Dept. of Chemicals & Petrochemicals. Ministry of Chemicals & Fertilizers, Govt. of India Plot No. 7P. Hi Tech Defence and Aerospace Park (IT Sector), Jala Hobli, Bengaluru - 562 149 E-mail: apddrl@cipet.gov.in

Head Office: CIPET, Guindy, Chennai - 600032



CIPET/SARP-APDDRL/Testing/2023-24/3122

Date-21.06.2023

To.

M/s. Namas Polymers #17, Sree Bakkesh Rice Industries Lokikere Road Davangere-577007

Sub: Test Report- Reg.

Ref. No:

1) Email dated 27.09.2022 & SSF dated 12.10.2022

2) Interim Test Report No. 23016 dated 17.04.2023

Dear Sir.

With reference to the above, the submitted sample was analyzed as per ISO 17088:2021. The summary detail of testing & analysis is given below:

Company Name & Address

: M/s. Namas Polymers

#17, Sree Bakkesh Rice Industries Lokikere Road Davangere-577007

Test Standard

: ISO 17088:2021

Sample Details Test Report No : "Film Pieces" - As stated by the party : 23016 (Final) & dated 21.06.2023

Date of Receipt of sample

: 12.10.2022

Date of Initiation

19.11.2022

14.06.2023

Date of Completion

92.37 %

Percentage of Compostability In 143 days

Requirement of Compostability in

180 days as per ISO 17088:2021

: 90 %

The sample submitted by M/s. Namas Polymers, is compostable and the percentage of compostability in 143 days reported vide test report No.23016 is 92.37 %.

The submitted sample also complies with the terms of Compostability, Seed germination and Disintegration as per ISO 17088:2021

Thanks & Regards,

Authorized Signatory 21.06.2028

Encl Analysis Report

केन्द्र : अहमदाबाद, अमृतसर, औरंगाबाद, अगरतला, बद्दी, बालासोर, बेंगलुरू, भोपाल,भुवनेश्र्वर, चन्दपुर, चेन्नै, देहरादून, गुरूग्राम, गुवाहाटी, ग्वालियर, हैदराबाद, हाजीपुर, हल्दिया, इम्फाल, जयपुर, कोच्चि, कोरब, लखनउ, मदुरै, मुरथल, मैसूरु, रायपुर, रॉची, बलसाड एवं विजयवाडा

Centres: Ahmedabad, Amritsar, Aurangabad, Agartala, Baddi, Balasore, Bengaluru, Bhopal, Bhubaneswar, Chandrapur, Chennai, Dehradun, Gurugam, Guwahati, Gwalior, Hyderabad, Hajipur, Haldia, Imphal, Jaipur, Kochi, Korba, Lucknow, Madurai, Murthal, Mysuru, Raipur, Ranchi, Valsad & Vijayawada.